



PRODUCT TYPE

Performance HPL

DIMENSIONS EN 315

Dimensions	Lenght	2440
	Width	1220
	Thickness	15
	Laver	1+9+1

WOOD SPECIES

Finish	HPL
Face	Poplar Panel
Long grained veneer	Poplar Panel
Short grained veneers	Poplar Panel

DENSITY EN 323

Density average	473-557	Kg/m ³
-----------------	---------	-------------------

BENDING STRENGTH EN 310

Modulus of Elasticity (Long Grained)	5426-6354	N/mm ²
Modulus of Elasticity (Short Grained)	4806-5864	N/mm ²

BONDING QUALITY EN 314

Class 1	OK
---------	----

MOISTURE CONTENT EN 322

% Moisture content	[6% -14%]
--------------------	------------

FORMALDHEYDE EMISSION EN12460-3

Classification E1	< 3.5 mg HCHO/(hm ²)
-------------------	----------------------------------

FIRE RESISTANCE EN 13501-1

Classification	D-s2, d0
----------------	----------